



# CLASSIC ACRYFIX SBR

## Waterproof Polymer Bonding aid and mortar Additive

### **PRODUCT:**

**Classic Acryfix SBR** is a milky, white liquid produced from styrene butadiene consists of microscopic particle of synthetic rubber.

### **COMPOSITION:**

**Classic Acryfix SBR** is styrene butadiene co-polymer latex specially designed for use with cement mix.

### **ADVANTAGES:**

Develops excellent bond with most building materials.  
Outstanding water resistance.  
Reduces or prevents salt penetration into concrete.  
Good chemical resistance.  
Highly durable in continuous wetting conditions.  
Increases flexibility.

### **DOSAGE:**

Typically 10 – 20% w/w on the OPC weight i.e., 5 – 10 kg per 50 kg of OPC.

### **USES:**

Concrete Repair, Floor screeds and Toppings, External Rendering, General concrete repairs. Protection of concrete against corrosion, salt attack, etc. Waterproofing of basements, toilets, terraces, roofs, swimming pools, water towers, etc. Fixing brick slip and tiles, Corrosion Protection of steel.

### **PACK:**

1kg, 5kg, 10kg, 20kg, 50kg, & 100kg containers.

### **DESCRIPTION:**

**Classic Acryfix SBR** has been specifically developed as an admixture for cement-based building materials. It is designed to improve the physical, mechanical and chemical resistance properties both in the fresh and hardened state. **Classic Acryfix SBR** has a strong plasticizing effect on cementitious mixes, thereby allowing a reduction in water: cement ratio which results in reduced permeability of the hardened materials.

**Classic Acryfix SBR** gives good early strength development, and improved flexural, compressive and adhesive strengths. Use of a primer coat of cement slurry containing **Classic Acryfix SBR** is an excellent method of achieving superior adhesive bond strengths.

### **TYPICAL PROPERTIES:**

Specific Gravity	1.02to 1.05@ 27°C
pH	7 to 10
Volatility	50%
Water vapour	
Permeability	Less than 4gm/m <sup>2</sup> /24hr through a 11mm thick test piece.
Shrinkage during cure	0.01% to 0.02%
Resistance to water	Excellent

Under pressure -30mm  
Head

no water penetration  
through a 15mm thick Test piece.

***INSTRUCTIONS FOR USE:***

***Surface Preparation:***

Prior to application of ***Classic Acryfix SBR***, all surfaces must be prepared properly to avoid failure. The surfaces shall be cleaned to remove all dust, foreign loose materials or any deposits of contaminants, which could affect the bonds between the surface and the ***Classic Acryfix SBR*** coating. This can be done by scarifying, grinding, water blasting, sand blasting and acid washing or by any other approved method.

All concrete surfaces shall be thoroughly pre-wetted for at least one hour prior to the application of ***Classic Acryfix SBR*** coating by ponding of water on flat surfaces and by vigorously spraying water on vertical / inclined surfaces.

When placing ***Classic Acryfix SBR*** coating, all water shall be removed so that surface is only damp or surface dry. In no case should there be standing water or a shiny wet surface.

***APPLICATION:***

3kg - 5kg of cement is mixed with 1kg of ***Classic Acryfix SBR*** and the mix has to be stirred thoroughly until no air bubbles remain in the mix and any lump found in the mix should be removed. If necessary, little water can be used to obtain the required consistency. The mix has to be applied by brush on rendered or prepared surfaces. Two or more coats are recommended. First coat should be allowed to air dry. The surface should be made wet before application in case of porous structures.

Note: ***Classic Acryfix SBR*** can be directly applied over the surfaces and coverage depends upon the surface conditions Approximately 1 kg covers 2 Sq.mt for 2 coats.

***STORAGE LIFE:***

Atleast one year in manufacturer's undamaged, sealed containers, when stored in dry, frost-free conditions.

***HANDLING PRECAUTIONS:***

***Classic Acryfix SBR*** is non-toxic but is mildly alkaline. Splashes to the skin should be removed with clean water.



PRIMADON CONSTRUCTION PRODUCTS PVT. LTD.  
F-C2, Sri Sai Raj Apartments, Indian Airlines Colony, Trimulgherry,  
Secunderabad - 500015, AP, India.